

Note on English translation:

This is a translation of the technical data sheet valid in Iran.

All stated details and properties are in compliance with the regulations of the Iran standards and building regulations. They are only applicable for the specified products, system components, application rules, and construction details in connection with the specifications of the respective certificates and approvals. Kplus denies any liability for applications outside of Iran as this requires changes acc. to the respective national standards and building regulations.



Technical Data Sheet

2022-2023

DECOPLAST

Finishing plaster

Product description

Decoplast is a very fine white hand applied gypsum stucco. Its fineness and limited setting time allow for easy and speedy application without wastage. A dense bright white smooth surface is always achievable with decoplast.

Storage

Store the bags on wooden pallets in a dry environment. Seal damaged and open bags airtight and use first. Can be stored for approx. 6 months.

Field of application

This product is used for producing precast decorative elements.

- finishing and skin coating walls or ceiling.

Properties and added value

- Powdery, ready-to-mix
- Gypsum based
- Lump-free mixing
- Stiff creamy, pliable consistency
- Good adhesive properties
- High yield
- Quick development of hardness
- Sufficient application time
- High water retention capacity
- White color

Application

Substrate pretreatment

Oil, dust, dirt and loose particles should be removed from the surface before application.

Mixing

Fill a clean empty container with sufficient amount of water and sprinkle Decoplast in clean, cold water until just below the water line. 1kg of Decoplast in 1.5 liter of water, applied as pre-cast decorative element: 1kg of Decoplast in 0.7 liter of water. Mix to a stiff creamy consistence without further additives using a margin trowel.

Wait 2-3 minutes for the floating gypsum to sink by soaking. Mix water and gypsum with hand or with a mechanical mixer at a low

speed until a proper mixture is obtained.

Do not mix this product with other materials as it may significantly change the properties.

Application

■ The tools to be used in application and container, in which Decoplast is to be mixed, should be clean and free of any particles.

■ Any impurities such as salt or gypsum as well as high water temperature will reduce the workability time and surface hardness.

Application time

■ Approx. 10minutes until initial setting.

■ Do not apply at room or substrate temperatures below +5 °C.

Technical specifications

Description	Unit	Value
Working time	minute	approx.10
Initial setting time	minute	7-12
Final setting time	minute	max.30
Approx. coverage (1 mm Thickness)	kg/m ²	0.7
Compressive strength	N/mm ²	>2.0
Flexural strength	N/mm ²	>1.0
Adhesive strength	N/mm ²	>0.1

Packaging

Product	Weight (kg)	Packaging (pcs./pallet)	Material Number
DECOPLAST	30	40	7041113001

Kplus Direct: Technical Support Dept.

- ▶ Phone: (+98 21) 88207929
- ▶ Fax : (+98 21) 88203126
- ▶ technical@kplus.ir

All technical changes reserved. Only the current printed instructions are valid. Our warranty is expressly limited to our products in flawless condition. All application quantities and delivery amounts are based on empirical data that are not easily transferable to other deviating areas. The stated information represents current state-of-the-art Kplus technology. The entire state of approved engineering rules, appropriate standards, guidelines, and rules of craftsmanship are not included herewith. These and all application instructions have to be adhered to separately by the installer.

All rights reserved. All amendments, reprints and photocopies, including those of excerpts, require the express permission of Kplus.

Head Office: